



PG-511 PRIMER GRAFIATO



PACKAGING

5 kg/20 kg



DRYING TIME

24 Hours



CONSUMPTION

0.2-0.25 kg/m²

Product Description

PG-551 is a white pigment primer, suitable for undercoating paintings of a surface, prior to the application with GF-22 or GS-11. It can also be used for other types of plasters. Its production is based on acrylic binders and mineral fillers.

Use

Primer PG-551 gives to the surface the same level of absorption. It has a big penetration and resistance. After the application of PG-551, the water absorption on the surface will be much lower.

Application

Do not apply to very cold or damp surface, in damp humid condition and in temperature under 5°C(41°F).

It is ready to use or can be diluted with just a little water. Apply with roller or shovel.

Consumption

Depending on the surface and from the film thickness 0.2 – 0.25kg/m².

Tools

Clean the equipment with water, immediately after the job.

Package

5kg and 20kg.

TECHNICAL DATA (IN +23°C AND 50% U.R.)

Form	Paste
Colour	White
Storage	12 months when stored in the original sealed packaging in a dry place.
Density (EN ISO 2811, DIN 53217, ASTM D 1475)	1.65-1.75 g/cm ³
Viscosity (RVDV -2T, R7)	5500-6500 cp
pH	≥8
Resistance against humidity	Dry after 24 hours in normal condotions
Application Temperature	(+5°C) - (+35°C)
Shear Stress (RVDV -2T, R7)	10000-15000 newton/m ²
% (RVDV -2T, R7)	10-70%
Kinematic Viscosity (RVDV -2T, R7)	2000-5000 mm ² /s