



GS-11 GRAFIATO STRUCTURE



PACKAGING

25 kg



DRY TIME

24 Hours



CONSUMPTION

1mm=2 kg/m²
1.5mm=3 kg/m²
2mm=3.6 kg/m²

Description

GS-11 GRAFIATO STRUCTURE is an acrylic ready for use, top coat plaster. It has an elastic structure as well as durability for facades over the thermal insulation system and the bottom plaster. It has a high resistance to atmospheric conditions. GS-11 GRAFIATO STRUCTURE offers exceptional processing quality.

Surface Preparation

Surfaces must be clean from dust and grease. It is recommended to paint first the surface with primer PG-551 PRIMER GRAFIATO.

Application

Do not apply to very cold or damp surface, in damp humid condition and in temperature under 5°C (41°F).

Apply easily with shovel and dilute it with water just 2%-4%.

Consumption

Depending on its severity. For 1mm it consumes approximately 2kg/m², 1.5mm about 3kg/m² and 2mm about 3.6 kg/m².

Drying Time

In good drying conditions, the partial dry after 24 hours and final dry after 14 days.

Tools

Clean the equipment with water, immediately after the job.

Package

25kg.

TECHNICAL DATA (IN +23°C AND 50% U.R.)

Form	Paste
Colour	White
Storage	12 months when stored in the original sealed packaging in a dry place.
Density (EN ISO 2811, DIN 53217, ASTM D 1475)	1.7-2.0 g/cm ³
Viscosity (RVDV -2T, R7)	15000-30000 cp
pH	≥8
Resistance against humidity	Dry after 24 hours in normal condotions
Application Temperature	(+5°C) - (+35°C)
Shear Stress (RVDV -2T, R7)	30000-600000 newton/m ²
% (RVDV -2T, R7)	10-90%
Kinematic Viscosity (RVDV -2T, R7)	5000-10000 mm ² /s

CONSUMPTION

1mm	2kg/m ²
1.5mm	3kg/m ²
2mm	3.6kg/m ²