# MATIS



# MA - 215 MATIFAST











## **Description**

MA-215 MATIFAST is a high-performance, fast drying, polymer-modified, cement-based tile adhesive with no vertical slip. It provides high initial and final adhesion strength and moisture resistance.

#### **Properties**

- -Perfect adherence.
- -Fast drying.
- -Can be applied on vertical surfaces even for bonding heavy tiles.
- -Can be applied easily.

## **Application**

- -Substrates must be sound, free from oil, grease and sufficiently dry. Cementitious substrates must be cured.
- -Use repairing mortar in case of uneven substrates to get a sound and flat surface.
- -Wipe the back side of tiles with water if dusty.
- -Pour 25 kg of MA-215 MATIFAST into 6 7L of clean water slowly and mix to obtain a homogeneous paste free from lumps. A low-speed mixer is recommended to mix. Do not add any additive which is not mentioned in the instructions for the application.
- -Allow to stand for 5 minutes to mature. After 1-2 minutes remixing, the paste is ready for application.

- -Consumption is 3-5 kg/m2.
- -Consume the prepared mortar within 45 minutes.
- -Spread the mortar onto the substrate with a notched trowel, the notch size of which is appropriate to the tile dimension. To obtain a good adhesion, first apply a thin coat of the mortar with the flat side of the trowel, then notch with the toothed side of the trowel.
- -Open time is 10 minutes. Install the tiles within this period with firm pressure. Unfavourable climatic conditions (high temperature, low humidity, wind, etc.) can reduce this time to just a few minutes. If this period is exceeded, scratch and discard the mortar.
- -Clean tools and hands with water, surfaces with a damp cloth.
- -Tiles installed with MA-215 MATIFAST must not be subject to water for at least 3-4 hours.
- -Product application temperature and storage conditions should be between +5°C and +35°C.

#### **Shelf Life**

12 months when stored in the original sealed packing in dry place.

#### **Storage**

Store in dry medium. Do not stack more than 10 bags on top of each other.



## SCHEDA TECNICA (A +23°C E 50% RH.)

Forme	Polvere
Colore	Grigio/Bianco
Magazzinaggio	12 mesi se conservato
	nell'originale
	confezione sigillata in un luogo
	asciutto.
Rapporto di miscelazione	6-7L / 25 kg
Temperatura di Applicazione	(+5°C) - (+35°C)
Spessore di applicazione	Fino a 10 mm
Vita in vaso	45 minuti
Scivolamento (EN 12004-2)	≤0.5mm
Tempo Aperto (EN 12004-2)	Dopo 30 minuti ≥ 0,5 N/mm <sup>2</sup>
Forza di adesione a trazione (EN	
12004-	
2)	
<ul> <li>Forza di adesione a trazione precoce</li> </ul>	Dopo 6 ore ≥ 0,5 N/mm2
- Dopo l'esposizione al calore	≥ 1 N/mm <sup>2</sup>
- Dopo l'immersione in acqua	≥ 1 N/mm <sup>2</sup>
- Dopo i cicli di	≥ 1 N/mm <sup>2</sup>
congelamento/scongelamento	
Deformabilità (EN 12002)	≥ 2,5mm – S1 Deformabile
Intervallo di temperature di servizio	(-40°C) - (+80°C)
Reazione al fuoco	A1
Sostanze pericolose	Vedi scheda di sicurezza