

MA-255 ADESIPRO A10

Visokoperformansna, polimerno-modifikovana, cementna lepljiva masa za pločice sa produženim vremenom otvaranja i bez vertikalnog klizanja sa Fiber Strength Tech tehnologijom.



PAKOVANJE
25kg



ODNOSI MEŠANJA
7.75-8.25 L/25kg



POTROŠNJA
3-5 kg/m²

Opis

MA-255 ADESIPRO A10 je visokoperformansna, polimerno-modifikovana, cementna lepljiva masa za pločice sa produženim vremenom otvaranja i bez vertikalnog klizanja, sa Fiber Strength Tech tehnologijom. Pruža visoku početnu i finalnu snagu prijanjanja i otpornost na vlagu.

Područje primene

Koristi se za lepljenje unutrašnjih keramičkih pločica na podovima i zidovima, uključujući upijajuće i neupijajuće pločice, kao što je porcelan, na različite podloge kao što su beton, zidne opeke, itd. Može se koristiti za lepljenje granita, prirodnog kamena i dekorativnih cigli na raznim podlogama kao što su beton, zidne opeke, itd. u zatvorenom prostoru.

Priprema podloge

Površina koja treba da se prekriva pločicama treba da bude čista, bez prašine, masti, labavih čestica, boja, itd. Preporučuje se da se površina navlaži pre nanošenja. Koristite MATIART maltere za popravke u slučaju neravnih podloga, kako biste dobili ravnu površinu. Ako je prašnjava, obrišite poledinu pločica vlažnom krpom.

Primena

MA-255 ADESIPRO A10 se polako dodaje u vodu uz kontinuirano mešanje, dok se ne formira homogena pasta. Preporučuje se mešač sa niskim brojem obrtaja za mešanje. Mešavinu treba ostaviti da odstoji oko 10 minuta, pre nego što je ponovo kratko promešate. Da biste dobili dobro prijanjanje, nanesite malter na podlogu ravnim delom gletera, a zatim ga zupčastim delom gletera obradite. Veličina zupaca treba da bude odgovarajuća dimenzijama pločica. Pločice postavite na zupčasti malter unutar ovog perioda uz čvrst pritisak. Nepovoljni klimatski uslovi (visoka temperatura, niski nivo vlažnosti, vetar, itd.) mogu skratiti ovaj period. Ako se prekorači ovo vreme, skinite i odbacite malter. Pločice postavljene sa MA-255 ADESIPRO A10 ne smeju biti izložene vodi najmanje 24 časa.

Consumption

Potrošnja je 3-5 kg/m² u zavisnosti od površine.

Karakteristike



Tehnički podaci (IN +23°C I 50% U.R.)

Forma	Puder
Boja	Grej/Bela
Skladištenje	12 meseci ako se čuva u originalu zatvoreno pakovanje na suvom mestu.
Odnos mešanja	6.75-7.5 L / 25 kg
Temperatura primene	(+5°C) - (+35°C)
Debljina nanošenja	Do 10 mm
Život u vazi	4 sati
Klizavo (EN 12004-2)	≥ 0.5
Otvoreno vreme (EN 12004-2)	Posle 30 minuta ≥ 0,5 N/mm ²
Zatezna snaga veze (EN 12004-2)	
- Inicijal	≥ 1 N/mm ²
- Nakon izlaganja toploti	≥ 1 N/mm ²
- Nakon potapanja u vodu	≥ 1 N/mm ²
- Nakon ciklusa zamrzavanja/odmrzavanja	≥ 1 N/mm ²
Opseg radne temperature	(-40°C) - (+80°C)
Reakcija na vatru	A1
Opasne supstance	Pogledajte bezbednosni list

MATIS Construction Chemicals

Tiranë, Albania

info@matis-eu.com

www.matis-eu.com

T: +355 69 20 94 570

THIS TECHNICAL DATA SHEET SUPERSEDES ALL PREVIOUS EDITIONS RELEVANT TO THIS PRODUCT

2/2

DISCLAIMER: The above technical data, information, recommendations and guidance are based on scientific and technical knowledge, laboratory studies and long experience. However, the above information is considered to be as indicative and should be reviewed in any case in relation to each specific application conditions. Consequently, the suitability of each product in any application must be evaluated after referring to the updated Technical Data Sheet and to the website www.matis-eu.com, as well as after contacting the technical support department, in case of necessity. Our company guarantees the quality of the product itself, whilst in any case the user/applicant is exclusively responsible for any undesirable failures after using the product.