

MI-600 IZOBLOCK

Elastomerna, tečna vodonepropusna membrana za ravne krovove, krovove sa pločicama i kupatila.



PAKOVANJE

5kg/15kg



POTROŠNJA

2-2.5 kg/m²

Opis

MI-600 IZOBLOCK je elastomerna, tečna vodonepropusna membrana za ravne krovove i krovove sa pločicama. Posедуje visoku elastičnost i otpornost na vremenske uslove.

Područje primene

-Koristi se za vodonepropusnu zaštitu ravnih krovova, zakrivljenih krovova, kupatila, itd.

Priprema podloge

Površina treba da bude čista, bez prašine, masti, labavih čestica, boja itd. Preporučuje se da se površina navlaži pre nanošenja.

Za poboljšanje prijanjanja MI-600 IZOBLOCK-a na površinu, preporučuje se korišćenje MP-809 ACRYPRIME.

Primena

MI-600 IZOBLOCK se nanosi četkom ili valjkom u dva sloja, nakon što se prvi sloj MP-809 ACRYPRIME potpuno osuši.

Drugi sloj treba naneti nakon što se prvi sloj osuši. Vodonepropusna membrana MI-600 IZOBLOCK mora biti ojačana staklenom mrežicom u uglovima podova i u mestima spojeva.

Potrošnja

Potrošnja MI-600 IZOBLOCK-a je 2-2.5 kg/m², u zavisnosti od površine

Karakteristike



Tehnički podaci (IN +23 °C I 50% U.R.)

Forma	Zalepите
Boja	Bela/Grei
Skladištenje	12 meseci kada se čuva u originalnom zatvorenom pakovanju na suvom mestu.
Potrošnja	3-5 m ² /L
Temperatura primene	(+5°C) - (+35°C)
Maksimalna debljina za dva sloja	0.75-1 mm
Zatezna čvrstoca (EN 1542)	≥0.8 N/mm ²
Zatezna čvrstoca veze nakon termičkog starenja (EN 1062-11/EN 1542)	≥0.8 N/mm ²
Kapilarna apsorpcija vode (EN ISO 1063-3)	0.1kg/m ² h ^{0.5}
Most preko pukotina (EN 1062-7)(21 °C)	≥2.5mm (A5)/ ≥1.5mm (A4)
Reakcija na vatru	Cs1d0
Opasne supstance	Vidi SDS

MATIS Construction Chemicals

Tiranë, Albania
info@matís-eu.com
www.matis-eu.com
T: +355 69 20 94 570

THIS TECHNICAL DATA SHEET SUPERSEDES ALL PREVIOUS EDITIONS RELEVANT TO THIS PRODUCT

2/2

DISCLAIMER: The above technical data, information, recommendations and guidance are based on scientific and technical knowledge, laboratory studies and long experience. However, the above information is considered to be as indicative and should be reviewed in any case in relation to each specific application conditions. Consequently, the suitability of each product in any application must be evaluated after referring to the updated Technical Data Sheet and to the website www.matis-eu.com, as well as after contacting the technical support department, in case of necessity. Our company guarantees the quality of the product itself, whilst in any case the user/applicant is exclusively responsible for any undesirable failures after using the product.