

MT-550 MATIPLAST

Visokoučinkovita, polimerno-modifikovana, cementna žbuka za nivelisanje termoizolacionih ploča sa tehnologijom ojačanja vlaknima (Fibre Strength Tech).



PAKOVANJE
25kg



ODNOSI MEŠANJA
6-6.5 L/25kg



POTROŠNJA
1.5-3 kg/m²

Opis

MT-550 MATIPLAST je visokoučinkovita, polimerno-modifikovana, cementna žbuka za nivelisanje termoizolacionih ploča sa tehnologijom ojačanja vlaknima (Fibre Strength Tech).

Područje primene

-Koristi se kao osnovni sloj sa ojačavajućom staklenom mrežicom na fasadnim termoizolacionim pločama, čineći idealnu podlogu za sledeći sloj žbuke

Priprema podloge

Površina koja će biti pokrivena pločama treba da bude čista, bez prašine, masti, labavih čestica, boja itd. Preporučuje se da se površina navlaži pre nanošenja.

Primena

MT-550 MATIPLAST se polako dodaje u vodu uz stalno mešanje dok se ne dobije homogena pasta. Preporučuje se mešač sa niskim brojem obrtaja za mešanje. Mešavina treba da se ostavi da odstoji oko 5 minuta, a zatim ponovo da se lagano promeša. MT-550 MATIPLAST se nanosi glatkom trowel-om u maksimalnom debljini od 3-4 mm kao žbuka. Zatim se postavlja ojačavajuća staklena mrežica i čvrsto se ugrađuje u sveži osnovni sloj pomoću trowel-a.

Na kraju se površina zaglađuje i višak lepka se uklanja.

Potrošnja

Potrošnja je 1.5-3 kg/m², u zavisnosti od površine.

Karakteristike



Tehnički podaci (IN +23 °C I 50% U.R.)

Forma	Puder
Boja	Grei/Bela
Skladištenje	12 meseci ako se čuva u originalnom zatvorenom pakovanju na suvom mestu.
Odnos mešanja	6-6.5 litara vode / 25 kg
Temperatura primene	(+5°C) - (+35°C)
Lepljenje na termoizolacioni panel	Min. 0.08 N/mm ²
Apsorpcija vode	≤ 0.40 kg/m ² dk ^{0.5} W2
Čvrstoca na savijanje (EN 1015-11)	Min. 2 N/mm ²
Otpor na pritisak (EN 1015-11)	Min. 6 N/mm ²
Čvrstoca lepljenja očvrslog proizvoda Malteri za gips i gips (EN 1015-12)	Min. 0.5 N/mm ²
Opseg radne temperature	(-30°C) - (+80°C)
Reakcija na vatru	A1
Opasne supstance	Vidi SDS

MATIS Construction Chemicals

Tiranë, Albania

info@matis-eu.com

www.matis-eu.com

T: +355 69 20 94 570

THIS TECHNICAL DATA SHEET SUPERSEDES ALL PREVIOUS EDITIONS RELEVANT TO THIS PRODUCT

2/2

DISCLAIMER: The above technical data, information, recommendations and guidance are based on scientific and technical knowledge, laboratory studies and long experience. However, the above information is considered to be as indicative and should be reviewed in any case in relation to each specific application conditions. Consequently, the suitability of each product in any application must be evaluated after referring to the updated Technical Data Sheet and to the website www.matis-eu.com, as well as after contacting the technical support department, in case of necessity. Our company guarantees the quality of the product itself, whilst in any case the user/applicant is exclusively responsible for any undesirable failures after using the product.