

## MA-205 MATIBOND

High-performance, polymer-modified, cement-based tile adhesive with no vertical slip with Fibre Strength Tech.



**PACKAGING**  
25kg



**MIXING RATIO**  
6.75-7.5 L/25kg



**CONSUMPTION**  
3-5 kg/m<sup>2</sup>

### Description

MA-205 MATIBOND is a high-performance, polymer-modified, cement-based tile adhesive with no vertical slip with Fibre Strength Tech. It provides high initial and final adhesion strength and moisture resistance.

### Area of Use

-It is used for fixing interior ceramic floor and wall tiles to a variety of substrates such as concrete, brickwork, etc.

-It can be used for fixing granite tiles and non-absorptive wall or floor tiles on various substrates such as concrete, brickwork, etc. indoors.

### Substrate Preparation

The surface to be covered with boards should be free of dust, grease, loose particles, paints, etc. It is recommended to dampen it before application. Use MATIART repair mortars in case of uneven substrates, to get a flat surface. If dusty, wipe the back of the tiles with water.

### Application

MA-205 MATIBOND is slowly added to water under continuous stirring, until a homogeneous paste is formed. A low-speed mixer is recommended for mixing. The mixture should be left to rest for about 5-10 minutes before is stirred again for a bit.

To obtain a good adhesion, spread the mortar onto the substrate with the flat side of the trowel and notch with the toothed side. The notch sizes should be appropriate to the tile dimensions.

Install the tiles on the notched mortar within this period with a firm pressure. Unfavourable climatic conditions (high temperature, low humidity, wind, etc.) can reduce this time. If this period is exceeded, scratch and discard the mortar.

Tiles installed with MA-205 MATIBOND must not be subject to water for at least 24 hours.

### Consumption

It consumes 3-5kg/m<sup>2</sup> depending on the surface.

### Features



## Technical Data (IN +23° C AND 50% U.R.)

Form	Powder
Colour	Grey/White
Storage	12 months when stored in the original sealed packaging in a dry place.
Mixing Ratio	6.75-7.5 litres of water / 25 kg
Application Temperature	(+5°C) - (+35°C)
Application Thickness	Up to 10mm
Pot Life	6 Hours
Slip (EN 12004-2)	≤0.5mm
Open Time (EN 12004-2)	After 30 minutes ≥ 0.5 N/mm <sup>2</sup>
Tensile Adhesion Strength (EN 12004-2)	
- Initial	≥ 1 N/mm <sup>2</sup>
- After Heat Exposure	≥ 1 N/mm <sup>2</sup>
- After Immersion in Water	≥ 1 N/mm <sup>2</sup>
- After Freeze/Thaw Cycles	≥ 1 N/mm <sup>2</sup>
Service Temperature Range	(-40°C) - (+80°C)
Reaction to Fire	A1
Dangerous Substances	See SDS

### MATIS Construction Chemicals

Tiranë, Albania

info@matis-eu.com

www.matis-eu.com

T: +355 69 20 94 570